OA-W200

WOVEN GEOTEXTILE

OA-W200 is manufactured using high-tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. OA-W200 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	200 (890)
Grab Elongation	ASTM D 4632	%	15
Trapezoidal Tear (1)	ASTM D 4533	lbs (N)	75 (330)
CBR Puncture Resistance (1)	ASTM D 6241	lbs (N)	700 (3114)
Permittivity* (1)	ASTM D 4491	1/sec	0.05
Water Flow* (1)	ASTM D 4491	gpm/ft² (lpm/ft²)	5 (204)
Apparent Opening Size (AOS)* (2)	ASTM D 4751	US Sieve (mm)	40 (0.425)
UV Resistance	ASTM D 4355	%/hrs	70/500
TYPICAL ROLL DIMENSIONS			
Roll Dimensions		ft	12.5 x 432 15 x 360 17.5 x 309
Roll Area		yd²	600
Estimated Roll Weight		lbs	180

NOTES:

1. MARV = Minimum Average Roll Value.
2. Maximum average roll value as per ASTM D 4751.

Mullen Burst (ASTM D 3786) has been removed. It is not recognized by ASTM D 35 on Geosynthetics.
Puncture Strength (ASTM D 4833) has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture (ASTM D 6241).

***At the time of manufacturing. Handling may change these properties.**

This data is provided for informational purposes only. Ontario Agra Piping & Supplies makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check for current updates.

Ontario Agra Piping & Supplies

(905) 386-1744 sales @ontarioagra.ca **ontarioagra.ca**

Rev. March 2025